



Tradeflow Fibre Flex Leveller

**Fibre Reinforced, Flexible, Self Levelling Compound
3-50mm**

3-50mm Bed Depth / 20 mins Pot Life / 4 hours Foot Traffic / 4.0-4.4 Water

- Highly Flexible / Fibre Reinforced
- Self Levelling / Self Smoothing
- Free Flowing / Easily Pumped
- Excellent Wear Resistance
- Underfloor Heating
- Concrete / Screeds / Timber Floors
- Tiling / Vinyl / Soft Floor Coverings
- Interior / Exterior

DESCRIPTION

ROCATEX Tradeflow Fibre Flex Leveller is a free flowing, fibre reinforced, highly flexible, self levelling smoothing screed, blended from a mixture of the highest quality raw materials.

ROCATEX Tradeflow Fibre Flex Leveller can be applied in thicknesses from 3-50mm in a single pour. It provides an economic means of levelling and renovating existing interior floors prior to the installation of floor coverings including ceramic and porcelain tiles, natural stone, timber, vinyl and carpet. It is particularly effective for encasing underfloor heating systems where its thermal transfer properties enhance the heating application. Ceramic and porcelain tiles can be laid as soon as the product supports weight, i.e. approx. 4 hours.

ROCATEX Tradeflow Fibre Flex Leveller is suitable for use in domestic and commercial environments and also as a wearing surface. Suitable for use on exterior solid surfaces such as patios, walkways and balconies prior to the application of tiles. Please refer to Exterior Use section below.

PREPARATION

All installations should be carried out in accordance with BS 5385. All surfaces must be clean, firm, dry, free from all loose matter including dust, dirt, oil, grease, laitance and any other contaminants that may affect adhesion. All substrates should be prepared to provide a rigid and secure base without deflection and suitable to support the intended weight. New timber should be given time to find equilibrium with its surroundings.

The following information provides further details for preparing various common substrates. Unless stated otherwise, any reference to the term "diluted" means 1 part primer mixed with 1 part clean water. N.B. All primer applications should be fully dry before next works commence.

Anhydrite Screeds - The substrate must not leach moisture. Anhydrite screeds must not have a moisture content greater than 0.5% or 75% relative humidity (RH). This can easily be tested by taking moisture readings across the whole surface. It is essential that surface laitance is removed in accordance with the screed manufacturer's recommendations, followed by vacuum cleaning to remove any loose material, then apply 2-4 neat coats of ROCATEX Acrylic Primer or 2 diluted coats of ROCATEX Ultimate Grip Primer.

Concrete Screeds - Prime with 2 diluted coats of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before levelling can commence is approximately 6 weeks.

Power Floated Concrete - The cured surface should be mechanically abraded to remove any curing agents and open up the surface, followed by vacuum cleaning to remove any loose material, then apply 2 diluted

coats of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before tiling can commence is approximately 6 weeks.

Sand & Cement Screeds - Prime with 2 diluted coats of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before levelling can commence is approximately 3 weeks.

Plywood Overlay - Internal use only. Must be a minimum thickness of 15mm, Class 3 exterior grade, screwed down to existing boards and joists with staggered joints at 300mm centres and 150mm centres along board edges. Prime all edges and underside with 1 neat coat of ROCATEX Acrylic Primer or 1 neat coat of ROCATEX Ultimate Grip Primer. Prime the surface with 1 diluted coat of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer. N.B. All timber constructions must be adequately ventilated behind to prevent atmospheric moisture distortion and warpage of the boards.

Tongue & Grooved Boards/Floorboards/Chipboard - Internal use only. Must be overboarded with suitable tile backer board/plywood. N.B. All timber constructions must be adequately ventilated behind to prevent atmospheric moisture distortion and warpage of the boards.

Cement Based Tile Backer Boards - Prime the surface with 1 diluted coat of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer.

Existing Tiles & Other Non-Porous Substrates - Apply 1 neat coat of ROCATEX Ultimate Grip Primer.

Flooring Grade Asphalt - Ensure the surface is in good condition and there are no signs of debonding and/or hollowness. Apply 1 neat coat of ROCATEX Ultimate Grip Primer. N.B. No single pour should be deeper than 6mm and no more than 2 layers should be applied. Once the first layer is dry, apply 1 diluted coat of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer.

Epoxy Damp Proof Membranes - Apply 1 neat coat of ROCATEX Ultimate Grip Primer.

Underfloor Heating Systems - Existing underfloor heating must be switched off at least 3 days prior to applying ROCATEX Tradeflow Fibre Flex Leveller to allow the substrate to cool. Once application has been completed allow 2 weeks before turning the heating system back on. Start with a low temperature and gradually increase by 5°C per day.

Electric Underfloor Heating - When encasing new electric underfloor heating, the system must be turned off. Allow 2 weeks before turning the heating system back on. Start with a low temperature and gradually increase by 5°C per day.

Heated Screeds - Prior to applying ROCATEX Tradeflow Fibre Flex Leveller, underfloor heated screeds should be commissioned in line with the heating system/screed guidelines. The heating system must be switched off at least 3 days prior to application to allow the substrate to cool. Once application has been completed allow 2 weeks before turning the heating system back on. Start with a low temperature and gradually increase by 5°C per day.

MIXING

Mix 20kg of ROCATEX Tradeflow Fibre Flex Leveller in a clean mixing vessel with 4.0 - 4.4 litres of cold clean tap water until a smooth, homogenous consistency is achieved using a suitable drill with whisk attachment. Mix at a slow speed for a minimum of 3 minutes to ensure that all ingredients are dispersed thoroughly throughout the whole mix.

APPLICATION

Once mixed, the material is immediately ready for use and has a working time of approximately 15 - 20 minutes. If the mix stiffens before it has been poured, it must be discarded. Do not add extra water.

The mixed material is poured onto the prepared subfloor and spread with a smooth edge trowel to the required thickness in one operation. Alternatively the use of a spiked roller will ensure a smooth even finish that will not require any further attention prior to the floor coverings being applied.

ROCATEX

Rocatex Ltd
3+4 Camwal Park
Camwal Road
Harrogate, HG1 4PT

T: +44 (0)1423 882 990
F: +44 (0)1423 299 040
E: info@rocatex.com
www.rocatex.com

This information is offered without guarantee. Our Company policy is one of continuous research and development, we therefore reserve the right to update this information at any time without prior notice. We guarantee the consistent high quality of our products, however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof. If in doubt, conduct a small test or obtain further technical advice.

When pumping ROCATEX Tradeflow Fibre Flex Leveller check the material flow regularly to ensure the correct consistency of material is being achieved.

The minimum temperature at which the product should be laid is 5°C with a maximum of 25°C. Air and subfloor temperatures should exceed 5°C for one week after application. Setting and hardening times will vary depending on temperature and ventilation. Setting and hardening times will be shortened at high temperatures and extended at low temperatures. Adequate ventilation is essential during the drying process but draughts must be eliminated to avoid uneven drying patterns.

No more than 2 layers should be applied. Once the first layer is dry, apply 1 diluted coat of ROCATEX Acrylic Primer or 1 diluted coat of ROCATEX Ultimate Grip Primer and allow to dry before applying a second layer.

Ceramic and porcelain tiles can be laid as soon as the product supports weight, i.e. approx. 4 hours. Soft floor coverings may be laid after 12 hours and natural stone after 24 hours.

Exterior Use - ROCATEX Tradeflow Fibre Flex Leveller is suitable for exterior use when used below a tile installation. All subfloors must be solid and have an effective damp-proof membrane. Do not apply if temperatures are likely to drop below freezing within 7 days of application. Ensure air and subfloor temperature is above 5°C and that freshly applied levelling compound is protected from rain, frost, high temperatures and conditions causing rapid drying for 7 days.

COVERAGE

For every 1mm thickness 1.7kg of dry powder per square metre will be required, i.e. 1m² at 10mm thickness will require 17kg of dry powder.


STORAGE


Store unopened clear of the ground in a cool, dry, frost free environment.

TECHNICAL DATA

Conformity:	Conforms to the requirements of BS EN 13813 CT C35 F9 and BS EN 13892-4 AR1
Application temperature:	5°C to 25°C
Bed thickness:	3-50mm
Mixing ratio:	4.0 - 4.4 litres of clean tap water to 20kg of powder
Pot life:	15 - 20 minutes at 20°C
Walk on time:	4 hours at 20°C
Floor coverings:	4 hours at 20°C - ceramic & porcelain
(at 3mm thickness)	12 hours at 20°C - soft floor coverings
	24 hours at 20°C - natural stone
Final hardening:	28 days at 20°C
Pump application:	Yes
Pack sizes:	20kg
Shelf life:	12 months in cool dry area

Note: All times refer to site conditions of 20°C and 50% relative humidity. These times will be increased at lower temperatures and reduced at higher temperatures.


Rocatex Ltd., UK www.rocatex.com
21 DoP No. 010 EN 13813 / EN 13892-4
CT C35 F9 / AR1


Rocatex Ltd., UK www.rocatex.com
21 DoP No. 010-UK EN 13813 / EN 13892-4
CT C35 F9 / AR1

HEALTH & SAFETY



DANGER



CONTAINS CHROMIUM (VI)

DANGER Causes skin irritation. Harmful if swallowed. Causes serious eye damage. May cause respiratory irritation. Keep out of reach of children. Avoid breathing dust. Wear protective gloves and eye protection. Wash hands thoroughly after handling. IF SKIN IRRITATION OCCURS: Get medical advice/attention. IF SWALLOWED: Call a poison centre or doctor/physician if you feel unwell. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a poison centre or doctor/physician. Dispose of contents/container in accordance with local/regional regulations. Repeated exposure may cause skin dryness and cracking. **CONTAINS CHROMIUM (VI)** May produce an allergic reaction. To avoid risks to human health and the environment, comply with instructions for use. Safety data sheet available on request.